

# RG400 LSFH, 50 Ohm, 6 GHz, 105°C, ø5 mm, RADOX® jacket ENVIROFLEX\_400

## Properties

- Ozone, UV and weathering resistance
- UL AWM style 3651
- CPR qualified



## Construction

Component	Material	Detail	Diameter
Centre conductor	Copper, Silver plated	Strand-19	1 mm
Dielectric	SPEX (Crosslink Foam PE)		2.98 mm
Outer conductor	Copper, Silver plated	Braid, 96%	3.61 mm
Outer conductor	Copper, Silver plated	Braid, 94%	4.2 mm
Jacket	RADOX	black/bl line	5 mm - 0.1 mm

## Electrical data

Impedance	50 Ω +/-2Ω
Operating frequency	≤ 6 GHz
Capacitance	94 pF/m
Velocity of signal propagation	70.3 %
Signal delay	4.74 ns/m
Screening effectiveness	70 dB at frequency 0.001 GHz ... 6GHz
Insulation resistance	10000000 MΩ*m
Inner conductor resistance	29.45 Ω/km
Operating Voltage (at sea level)	≤ 2.5 kVrms
Voltage Rating UL	300 V
Phase vs temperature	10000 ppm at temperature -40 ... 100°C
Phase vs bending	0.5 °/GHz
Test voltage (50 Hz/1 min)	≤ 5 kVrms

## Mechanical data

Weight	approx. 6 g/m
Static bending radius	≥ 10 mm
Repeated bending radius	40 mm
Dynamic bending radius	< 40 mm

## RG400 LSFH, 50 Ohm, 6 GHz, 105°C, ø5 mm, RADOX® jacket

ENVIROFLEX\_400

### Mechanical data

Abrasion test	MIL-T-81490 - §4.7.19 - prod. II - modified
---------------	---

### Environmental data

Operation temperature	-40 °C ... 105 °C
Installation temperature	-20 °C ... 60 °C
CPR class	Eca
Flame propagation standard	EN 60332-1-2
	UL 1581 § 1100
	IEC 60332-1
Fire characteristics	free of halogenes, acc. standard IEC 60754
Smoke test	EN 61034-2
Ageing test	MIL-C-17 § 4.8.16
Cold bend test	MIL-C-17 § 4.8.19
UV resistance	IEC 60068-2-5, proc. C
Thermal stress test	IEC 61196-1 § 10.9
Toxicity test	NF X 70-100

### Additional Information

Railway certificates discontinued by end of 2017. Replacement type for railway: RADOX\_RF\_400.

### Suitable connectors

Cable group	U11
-------------	-----

### Ordering information

Item number	Item description	Available as assembly only
22512280	ENVIROFLEX_400	No

### Power Matrix

Calculation: typical Attenuation [ formula: (a\*f^0.5 + b\*f) ] and maximum Power CW [ formula: (p/f^0.5) ]

a coefficient typical =	<b>0.402</b>	b coefficient typical =	<b>0.142</b>
fmax =	<b>6</b>	P at 1 GHz =	<b>225</b>
Frequency	Nom. attenuation	Nom. attenuation	CW power
GHz	(dB/m)	(dB/ft)	(W)
	sea level 25°C ambient temperature	sea level 25°C ambient temperature	sea level 40°C ambient temperature
0.10	0.141	0.043	712
0.20	0.208	0.063	503
0.30	0.263	0.080	411
0.40	0.311	0.095	356
0.60	0.397	0.121	290
0.80	0.473	0.144	252
1.00	0.544	0.166	225
1.20	0.611	0.186	205
1.40	0.674	0.206	190
1.60	0.736	0.224	178
1.80	0.795	0.242	168
2.00	0.853	0.260	159
2.50	0.991	0.302	142
3.00	1.122	0.342	130
3.50	1.249	0.381	120

---

**RG400 LSFH, 50 Ohm, 6 GHz, 105°C, ø5 mm, RADOX® jacket**  
ENVIROFLEX\_400

<b>Power Matrix</b>			
4.00	1.372	0.418	112
5.00	1.609	0.490	101
6.00	1.837	0.560	92

HUBER+SUHNER is certified by ISO 9001, ISO 14001, ISO 45001, IATF 16949, AS/EN 9100 and ISO/TS 22163-IRIS. Waiver: Facts and figures herein are for information only and do not represent any warranty of any kind.  
DOCUMENT PIM-P1117 / Date of publication: 12.08.2024 / uncontrolled copy